

Purolite® MB400

Poliestireno Gel, Gel, Resina mixta,
Forma de hidrógeno, Forma hidróxido

PRINCIPALES APLICACIONES

- Desmineralización - lecho mixto
- Cartuchos

VENTAJAS

- Propósito general

SISTEMAS

- Sistema Cocorriente de regeneración
- Sistemas de Regeneración Contracorriente
- Lecho mixto
- Working Mixed Bed

APROBACIONES REGULADORAS

- Certificado Halal IFANCA

ENVASE TÍPICO

- Bolsa de 1 pie³
- Bolsa de 25 L
- Tambor (fibra) de 5 pie³

CARACTERÍSTICAS FÍSICAS Y QUÍMICAS:

Aspecto	Esferas	
Contenido de humedad (max.)	65 %	
Rango de tamaño de esferas	300 - 1200 µm	
< 300 µm (max.)	1 %	
Coefficiente de uniformidad (max.)	1.7	
Peso de envío (aprox.)	705 - 740 g/L (44.1 - 46.2 lb/pie ³)	
Límite de temperatura, lecho no Regenerable	100 °C (212.0 °F)	
Límite de temperatura, lecho Regenerable	60 °C (140.0 °F)	
Nombre del componente	Catiónica fuertemente ácida tipo gel	Anión Base fuerte Gel tipo I
Estructura del polímero	Gel reticulado poliestireno con divinilbenceno	Gel reticulado poliestireno con divinilbenceno
Grupo funcional	ácido sulfónico	Amonio cuaternario de tipo I
Forma iónica	forma H ⁺	OH ⁻ forma
Catión / anión relación volumétrica	40 %	60 %

Purolite, an Ecolab company, is a leading manufacturer of quality ion exchange, catalyst, adsorbent and specialty high-performance resins with global sales support.



We're ready to solve your process challenges.

For further information on Purolite products and services, visit www.purolite.com or contact us at the addresses below.

Americas
americas@purolite.com

Asia Pacific
asiapacific@purolite.com

EMEA
emea@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.