

Purolite® C120E

Poliestireno Gel, Resina Catiónica
Fuertemente ácida, Forma de sodio,
Grado de agua potable

PRINCIPALES APLICACIONES

- Ablandamiento - agua Potable
- Procesamiento de alimentos y bebidas

VENTAJAS

- Regeneración eficiente
- Buen funcionamiento cinético
- Bajos Extractraibles

APROBACIONES REGULADORAS

- Certificado Kosher

ENVASE TÍPICO

- Bolsa de 1 pie³
- Bolsa de 25 L
- Tambor (fibra) de 5 pie³
- Supersack de 1 m³
- Supersack de 42 pie³

CARACTERÍSTICAS FÍSICAS Y QUÍMICAS:

Estructura del polímero	Gel reticulado poliestireno con divinilbenceno
Aspecto	Esferas
Grupo funcional	ácido sulfónico
Forma iónica	Na ⁺ forma
Capacidad total (min.)	1.5 EQ/L (32.8 Kgr/pie ³) (Na ⁺ forma)
Retención de la humedad	56 - 60 % (Na ⁺ forma)
< 300 µm (max.)	1 %
Coefficiente de uniformidad (max.)	1.7
Hinchamiento reversible, Ca ²⁺ → Na ⁺ (max.)	12 %
Densidad específica	1.22
Peso de envío (aprox.)	770 - 805 g/L (48.1 - 50.3 lb/pie ³)
Límite de temperatura	120 °C (248.0 °F)

Purolite, an Ecolab company, is a leading manufacturer of quality ion exchange, catalyst, adsorbent and specialty high-performance resins with global sales support.



We're ready to solve your process challenges.

For further information on Purolite products and services, visit www.purolite.com or contact us at the addresses below.

Americas
americas@purolite.com

Asia Pacific
asiapacific@purolite.com

EMEA
emea@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.